

- [54] METHOD FOR IMPROVING THE CRIMPING OF POLYOLEFIN FILTER TOW
- [75] Inventors: Michael Hill, Ascot, England;
Walter A. Nichols, Richmond, Va.
- [73] Assignee: Filter Materials Limited, New York, N.Y.
- [21] Appl. No.: 231,148
- [22] Filed: Aug. 10, 1988
- [51] Int. CL⁵: D01D 5/22; D01D 5/42
- [52] U.S. CL: 264/25; 264/26; 264/147; 264/168; 264/563; 264/DIG. 47
- [58] Field of Search: 264/DIG. 47, 563, 25, 264/26, 147, 168; 28/257

- 3,726,079 4/1973 Feild et al. 57/155
- 3,739,053 6/1973 Yazawa 264/154
- 3,756,484 9/1973 Guenther 225/97
- 3,787,261 1/1974 Heger et al. 156/84
- 3,801,252 4/1974 Waterhouse 425/304
- 3,835,513 9/1974 Stanley 28/72.14
- 3,880,173 4/1975 Hill 131/269
- 3,883,936 5/1975 Stanley 28/72.14
- 3,927,957 12/1975 Chill et al. 425/131.11
- 3,949,454 4/1976 Irwin 28/72.14
- 3,985,600 10/1976 Blais 156/229
- 3,985,933 10/1976 Mehta et al. 428/357
- 4,129,632 12/1978 Olson et al. 264/40.1
- 4,133,087 1/1979 Li 28/257
- 4,133,088 1/1979 Hikobe 264/DIG. 47
- 4,134,951 1/1979 Dow et al. 264/147
- 4,273,600 6/1981 Luke 156/180

[56] References Cited

U.S. PATENT DOCUMENTS

- 2,914,810 12/1959 Robinson et al. 19/66
- 3,336,174 8/1967 Dyer et al. 264/DIG. 47
- 3,398,441 8/1986 Adachi et al. 264/DIG. 47
- 3,494,522 2/1970 Kim et al. 225/97
- 3,495,752 2/1970 Kim et al. 225/3
- 3,496,260 2/1970 Guenther et al. 264/156
- 3,500,517 3/1970 Dekker et al. 28/1.5
- 3,500,518 3/1970 Stanley et al. 28/1.6
- 3,500,627 3/1970 Kim 57/140
- 3,526,349 9/1970 Moro 225/97
- 3,565,308 2/1971 Slack 225/97
- 3,566,735 3/1971 Greene 83/344
- 3,577,724 5/1971 Greene 57/157
- 3,579,618 5/1971 Stewart et al. 264/DIG. 47
- 3,582,418 6/1971 Schuur 264/DIG. 47
- 3,595,454 7/1971 Kalwaites 225/3

FOREIGN PATENT DOCUMENTS

- 971878 10/1964 United Kingdom
- 1207733 10/1970 United Kingdom
- 1260957 1/1972 United Kingdom
- 1339496 12/1973 United Kingdom

Primary Examiner—James Lowe

Attorney, Agent, or Firm—Jeffrey H. Ingerman

[57] ABSTRACT

A method is provided for heating fibrillated polyolefin film prior to crimping, to improve the crimping, and thus the yield and variability as a filter, of the tow. The fibrillated tow is crimped while still hot from the heating step. The resulting fibers have more uniform crimping at higher levels than those not subject to heating.

19 Claims, 2 Drawing Sheets

